

Revision Date: 04.23.25



# 4 RUBBERIZED FLASHING CEMENT

## DESCRIPTION

**NC #4 Rubberized Flashing Cement** is a high grade rubberized flashing cement manufactured using quality chemical ingredients. **NC #4 Rubberized Flashing Cement** has a smooth trowelable consistency, excellent adhesion to wet surfaces, and great flexibility. Ideal for flashing details and a variety of waterproofing repairs such as roof penetrations and moving joints.

## USES

Specially formulated for use in damp, wet roofing situations. **NC #4 Rubberized Flashing Cement** can be used as a heavy duty flashing cement for repairing flashings, asphalt shingles, built-up roofs, metal and masonry surfaces. Great for sealing leaks and openings at flashings (chimneys, vents, skylights, metal joints, gutters). DO NOT USE with EPDM, PVC, TPO or other single-ply membranes.

## PREPARATION

Surface must be clean and free of dirt, dust, oil or grease and be free of any other foreign matter that would interfere with good adhesion. In colder climates we recommend storing the product at room temperature for 24 hours prior to application.

## APPLICATION

Apply with a trowel or putty knife. Spread **NC #4** to approximately 1/8" thickness and work thoroughly into the problem area. Repairing cracks and blisters: if the area is 1/4" wide to 2" long apply cotton or fiberglass fabric for reinforcement, then cover with additional cement.

## COVERAGE

Approximately 8 gallons per 100 sq. ft. (per coat)

## CLEANUP

Clean tools with a citrus cleaner or mineral spirits, taking necessary precautions when handling combustible liquids.

## CODE APPROVALS/COMPLIANCE

This product meets or exceeds the requirements of **ASTM 4586 Type I** and **ASTM D-3409, NYFD C. OF A. NO 4848**.



## QUICK INFO

### TOOLS NEEDED

Trowel

Spackle/Putty Knife

### SIZES AVAILABLE

5 Gallon Pail

### COVERAGE RATE

8 Gallons per

100 sq.ft. (per coat)

## PRECAUTION

DO NOT THIN. DO NOT HEAT CONTAINER. DO NOT store in an area where temperatures exceed 120°F.

V.O.C. Less than 300 g/L